



**Faculty of Mechanical Engineering**

**PRECEDING DEFORMATION EFFECTS ON THE CRUSH  
RESPONSE OF THE CIRCULAR CUP**

**Rosmia binti Mohd Amman**

**Master of Science in Mechanical Engineering**

**2018**

**PRECEDING DEFORMATION EFFECTS ON THE CRUSH RESPONSE OF THE  
CIRCULAR CUP**

**ROSMIA BINTI MOHD AMMAN**

**A thesis submitted  
in fulfilment of the requirement for the degree of Master of Science  
in Mechanical Engineering**

**Faculty of Mechanical Engineering**

**UNIVERSITY TEKNIKAL MALAYSIA MELAKA**

**2018**

## DECLARATION

I declare that this thesis entitled “Preceding Deformation Effects on the Crush Response of the Circular Cup” is the results of my own research except as cited in the references. The thesis has not been accepted for any degree and is not concurrently submitted in candidature of any other degree.

Signature : .....

Name : Rosmia binti Mohd Amman

Date : .....

## **APPROVAL**

I hereby declare that I have read this thesis and in my opinion this thesis is sufficient in terms of scope and quality for the award of Master of Science in Mechanical Engineering.

Signature : .....

Supervisor Name: Assoc. Prof. Dr. Sivakumar A/L Dhar Malingam

Date : .....

## **DEDICATION**

To my beloved parents, my father Mohd Amman bin Hassan and my late mother

Nurhaidah binti Bacho

To my loving and caring sisters, Nurhayati and Nurasyirah

To my beloved protecting brothers, Sabri, Muhammad Zulfadli, Mohd Asrul, Mohd Nur

Azwan, Mohammad Hairul Nizam and Mohd Faqrul Ikhwashah

## ABSTRACT

Automotive body structure is made up of formed components which have undergone plastic deformation during forming process that altered the structural behaviour of these components. Ignoring the preceding deformation effects in subsequent crush analysis could lead to inaccurate crashworthiness evaluation. In this study, the crush response of circular cup has been studied to quantify the effects of neglecting the preceding deformation effects such as geometrical changes and work hardening effects. The draw formed circular cups were fabricated through draw forming experiment on advanced high strength steel, dual-phase (DP600) steel with a nominal sheet thickness of 1.2 mm. Quasi-static crush experiment was subsequently performed on the draw formed circular cup to examine the preceding deformation effects on crush response. The draw forming simulation was performed at various punch speeds to investigate the geometrical changes and strain rates effect on deformation behaviour. An ideal computer-aided design (CAD) and draw formed cup model were used to develop finite element (FE) crush models in order to investigate the effects of geometrical changes and work hardening incurred during the draw forming process. The measured global load-displacement curve from experiments were used to validate the FE models developed using HyperWork. All draw forming and quasi-static crush experiments were simulated using Radioss solver employing Johnson-Cook constitutive model with isotropic hardening rule. The subsequent crush simulation was performed with and without incorporating mapped contour. Results show that draw forming process at various punch speeds affected the material strength and deformation behaviour of draw formed circular cup. In case of crush simulation without mapping (case A and case B), the geometrical changes from preceding draw forming process greatly affected the crush response of circular cup. The maximum force recorded at the end of crush process led to 46% and 15.2% higher for ideal CAD and draw formed cup geometry, respectively compared to the experiment. While in the case of with mapping (case 1 and case 2), work hardening effect resulted from draw forming process overcame the thinning effect and therefore made the structure stiffer and led to higher force value when compared to the case of without mapping. The percentage difference of maximum load recorded at the end of crush analysis with and without mapped residual contour was 12.9% and 3.8% for ideal CAD and draw formed cup model, respectively. Dynamic crush event showed higher response compared to quasi-static crush event in terms of load-displacement, stress and energy absorption behaviour by 45.5%, 40.7% and 30.7% respectively due to strain rates and inertia effects. Based on the crush response of the circular cup, the preceding deformation effects should be included in subsequent crush analysis by mapping the residual contour on draw formed geometry, instead on ideal CAD geometry in order to improve crashworthiness prediction.

## ABSTRAK

Struktur badan automotif terdiri daripada komponen yang terbentuk yang telah mengalami pembentukan plastik semasa proses pembentukan yang mengubah tingkah laku struktur komponen-komponen ini. Mengabaikan kesan pembentukan terdahulu dalam analisis mampatan seterusnya boleh membawa kepada ketidaktepatan penilaian keupayaan kenderaan untuk mengelakkan kecederaan penumpang semasa kemalangan. Di dalam kajian ini, tindak balas mampatan cawan bulat telah dikaji untuk mengukur kesan mengabaikan pembentukan terdahulu seperti perubahan geometri dan kesan pengerasan kerja. Cawan bulat yang terbentuk dihasilkan melalui eksperimen pembentukan pada kepingan besi termaju berkekuatan tinggi, besi dwi-fasa (DP600) dengan ketebalan 1.2 mm. Eksperimen pemampatan kuasi-statik kemudiannya dilakukan pada cawan bulat yang terbentuk untuk meneliti kesan pembentukan terdahulu pada tindak balas mampatan. Simulasi pembentukan dijalankan pada pelbagai kadar muatan untuk menyiasat perubahan geometri dan kesan kadar terikan pada sifat pembentukan. Model reka bentuk ideal CAD dan cawan yang terbentuk digunakan untuk membangunkan model unsur terhingga (FE) mampatan. Lengkuk beban-anjakan global diukur daripada eksperimen digunakan untuk mengesahkan model yang telah dibina menggunakan HyperWork. Semua eksperimen pembentukan dan pemampatan kuasi-statik disimulasikan menggunakan model menjujuk Johnson-Cook bersama dengan peraturan pengerasan isotropik. Simulasi pemampatan seterusnya dilakukan dengan dan tanpa menggabungkan pemetaan kontur. Hasil menunjukkan bahawa proses pembentukan pada pelbagai kadar muatan mempengaruhi kekuatan bahan dan sifat pembentukan cawan bulat yang telah terbentuk. Di dalam kes simulasi mampatan tanpa pemetaan (kes A dan kes B), perubahan geometri dari proses pembentukan terdahulu sangat mempengaruhi tindak balas pemampatan cawan bulat. Daya maksimum yang direkodkan pada akhir proses pemampatan membawa masing-masing kepada 46% dan 15.2% lebih tinggi untuk geometri ideal CAD dan cawan yang terbentuk, berbanding eksperimen. Manakala dalam kes dengan pemetaan (kes 1 dan kes 2), kesan pengerasan kerja yang terhasil daripada proses pembentukan mengatasi kesan penipisan dan mengakibatkan struktur menjadi lebih keras dan membawa kepada daya yang tinggi jika dibandingkan dengan kes tanpa pemetaan. Perbezaan daya tertinggi yang terhasil pada akhir proses pemampatan dengan dan tanpa pemetaan sisa kontur adalah masing-masing 12.9% dan 3.8% untuk model ideal CAD dan cawan yang terbentuk. Pemampatan dinamik menunjukkan tindak balas yang lebih tinggi berbanding pemampatan kuasi-statik dari segi beban-anjakan, tegasan dan penyerapan tenaga masing-masing 45.5%, 40.7% dan 30.7% disebabkan oleh kadar terikan dan kesan inersia. Berdasarkan tindak balas mampatan cawan bulat, kesan pembentukan terdahulu perlu dimasukkan ke dalam analisis pemampatan seterusnya dengan memetakan sisa kontur kepada geometri cawan bulat yang telah terbentuk, bukannya pada geometri ideal CAD.

## ACKNOWLEDGEMENTS

First and foremost, I would like to take this opportunity to express my sincere acknowledgement to my main supervisor Associate Professor Dr. Sivakumar A/L Dhar Malingam from Faculty of Mechanical Engineering Universiti Teknikal Malaysia Melaka (UTeM) for his essential supervision, guidance, moral support and encouragement towards the completion of this thesis.

Besides that, I also would really like to express my greatest gratitude to Dr. Ismail bin Abu Shah from Faculty of Engineering Technology, my co-supervisor of this project for sharing his knowledge with me and always giving me many meaningful advices that was really inspired me throughout conducting this project. I appreciate all his contributions of time and ideas to make my MSc experience productive and stimulating. Special thanks to my ex-supervisor Dr. Haryanti Samekto for being my mentor which always gives me positive energy, encourage me and show me a path in achieving my ambition to further my study.

I would also like to express my deepest gratitude to Encik Mohd Faizal bin Halim, our project's group leader for sharing his knowledge about this project. This work has been also partly performed with a financial grant from the Research Acculturation Grant Scheme (RAGS/1/2014/TK01/FTK/B00083), which is gratefully acknowledged for its financial support. Also special appreciation to Encik Saiful Naim bin Sulaiman and support team from ORS Technologies Sdn Bhd for their guidance and assistance in helping me on my simulation, model set up and analysis works. Last but not least, I would like to thanks to Encik Wan Saharizal bin Wan Harun, our friendly technician who always helps and guiding me when conducting my experimental works. Besides that, I also like to thank all my friends especially Noordiana binti Mohd Ishak, Kathiravan A/L Subramaniam, Ng Lin Feng, Fadzila binti Hussain and Naziatul Fazilah binti Mohd Zalani for supporting me in different ways during my study.

My special thanks go to my late mother, beloved father and siblings for their continuous moral support in completing this master. Thank you to everyone who had been involved either directly or indirectly on completing this project.



## TABLE OF CONTENTS

	PAGE
<b>DECLARATION</b>	
<b>APPROVAL</b>	
<b>DEDICATION</b>	
<b>ABSTRACT</b>	i
<b>ABSTRAK</b>	ii
<b>ACKNOWLEDGEMENTS</b>	iii
<b>TABLE OF CONTENTS</b>	iv
<b>LIST OF TABLES</b>	vii
<b>LIST OF FIGURES</b>	viii
<b>LIST OF APPENDICES</b>	xiii
<b>LIST OF ABBREVIATIONS</b>	xiv
<b>LIST OF PUBLICATIONS</b>	xv
 <b>CHAPTER</b>	
<b>1. INTRODUCTION</b>	<b>1</b>
1.1 Introduction	1
1.2 Background of study	1
1.3 Problem Statement	4
1.4 Research Objectives	5
1.5 Scope of Study	5
1.6 Significance of Study	6
1.7 Thesis Layout	6
 <b>2. LITERATURE REVIEW</b>	<b>8</b>
2.1 Introduction	8
2.2 Trends in Material for Vehicle Crashworthiness	8
2.3 Automotive Vehicle Body Structure	17
2.4 Sheet Metal Draw Forming Parts	21
2.4.1 Formability of Draw Forming Part	21
2.4.2 Formability Assessment	24
2.5 Mechanics of Large Plastic Deformation	26
2.5.1 Large Plastic Deformation in Sheet Metal Forming	27
2.5.2 Large Plastic Deformation in Crash Events	31
2.6 Strain Rate Effects	36
2.7 Johnson-Cook Strain Rate-Dependent Model	42
2.8 Finite Element Simulation of Crash Analysis	45
2.8.1 Forming History on Crash Analysis	46
2.8.2 Implicit and Explicit Time Integration	51
2.9 Summary	53
 <b>3. METHODOLOGY</b>	<b>55</b>
3.1 Introduction	55
3.2 Research Framework	55
3.3 Research Material	59
3.3.1 Material Properties	60

3.3.2	Johnson-Cook Constitutive Model	62
3.4	Experimental Procedures	65
3.4.1	Draw Forming Experiment	65
3.4.2	Crush Experiment	67
3.5	Finite Element Simulation of Draw Forming Process	68
3.5.1	FE Circular Cup Draw Forming Model	70
3.5.2	Mesh Convergence Study	77
3.5.3	Model Validation	78
3.6	Finite Element Crush Simulation	81
3.6.1	FE Circular Cup Crush Model	83
3.6.2	Results Mapping Process	85
3.6.3	Model Validation	88
3.7	Summary	89
<b>4.</b>	<b>RESULT AND DISCUSSION</b>	<b>90</b>
4.1	Introduction	90
4.2	FE Simulation of the Draw Forming at Various Punch Speeds	90
4.2.1	Mechanics of Deformation	91
4.2.2	FE Load-displacement Response	94
4.2.3	Stress and Strain Behaviour	95
4.2.4	Strain Rate at Various Locations	97
4.2.5	Thickness Change	98
4.2.6	Geometrical Difference between Ideal CAD and Draw Formed Circular Cup	100
4.3	FE Quasi-static Crush Simulation without Mapping Residual Contour	102
4.3.1	Mechanics of Deformation during Quasi-static Crush Experiment	102
4.3.2	Development of FE Crush Models without Mapping	104
4.3.3	Deformation Mode	106
4.3.4	Load-displacement Response	107
4.3.5	Stress and Strain Behaviour	109
4.3.6	Thickness Change	112
4.3.7	Energy Absorption Behaviour	114
4.4	FE Quasi-static Crush Simulation with Mapping Residual Contour	114
4.4.1	Development of FE Crush Models with Mapping	115
4.4.2	Deformation Mode	117
4.4.3	Load-displacement Response	118
4.4.4	Stress and Strain Behaviour	121
4.4.5	Thickness Change	124
4.4.6	Energy Absorption Behaviour	125
4.4.7	Dynamic Crush Behaviour with Mapped Residual Contour	126
4.4.7.1	Comparison of Load-displacement Response	126
4.4.7.2	Comparison of Stress and Strain Contour	128
4.4.7.3	Comparison of Energy Absorption Behaviour	130
4.5	Summary	131

<b>5. CONCLUSION AND RECOMMENDATIONS FOR FUTURE RESEARCH</b>	<b>134</b>
5.1 Conclusion	134
5.2 Recommendations for Future Research	136
<b>REFERENCES</b>	<b>137</b>
<b>APPENDICES</b>	<b>155</b>

## LIST OF TABLES

TABLE	TITLE	PAGE
2.1	Crashworthiness requirements for vehicle safety during collision	10
2.2	Summarization of draw forming mechanism	29
2.3	Typical strain rates for various process and applications	37
2.4	JC parameter value for material DP600 steel obtained from literature	45
3.1	Overall research methodology	57
3.2	Chemical composition of DP600 steel sheet (wt. %)	60
3.3	Material properties of DP600 at different strain rates	61
3.4	Basic mechanical properties of DP600 steel	62
3.5	Material input in FE simulation for parameters of JC	64
3.6	Comparison of geometrical shape and dimension of FE draw forming simulation and experiment at 8.333 mm/s	79
3.7	Mapping strategy to determine suitable FE mapping approach for crush analysis	87
4.1	Strain rates value at various locations for all applied punch speeds	98
4.2	Description of cases studied for investigating the geometrical effects on subsequent quasi-static crush analysis	104
4.3	Description of cases studied for investigating the mapping effects on subsequent crush analysis	117
4.4	Percentage difference of cup nose displacement for the case with and without mapping	118

## LIST OF FIGURES

<b>FIGURE</b>	<b>TITLE</b>	<b>PAGE</b>
1.1	Components of AUDI A5 body structure	3
2.1	Trends of steel material in the automotive industry for the past years	11
2.2	The material evolution in the automotive body structure	12
2.3	Relationship between strength and formability for various types of steel	13
2.4	Applications of DP steels in automotive industry	15
2.5	Schematic illustration of a typical microstructure of DP steel	16
2.6	Major vehicle structure components	17
2.7	Reinforcement components in BIW structures	19
2.8	Typical side structures of passenger cars	20
2.9	Categories of deformation mode in press forming of sheet steels	23
2.10	Factor affecting the formability of sheet metals	24
2.11	Load-displacement curve used as formability assessment during draw forming process	25
2.12	Deformation zones in cup draw forming process	28
2.13	The stress acted on the (a) flange region and (b) sidewall region	30
2.14	Load-displacement curve of large plastic deformation	31
2.15	Different zones in vehicle crash impact	32
2.16	The structural collapse of (a) axial and (b) s-rail crush structures	33
2.17	Comparison between static and dynamic tests	35
2.18	Typical behaviour of a stiffened panel subjected to longitudinal	36

	compressive loads	
2.19	Strain rate effect on yield strength at low and high loading rates	38
2.20	Strain rates effect on stress strain behaviour correspond to energy absorption value under static and crash conditions	40
2.21	Strain rate effect on yield stress and flow stress of DP600 steel loaded under strain rates $0.0001 \text{ s}^{-1}$ to $1600 \text{ s}^{-1}$	41
2.22	Strain rate effect on hardening rate of DP600 steel loaded under strain rates from quasi-static $0.01 \text{ s}^{-1}$ to $600 \text{ s}^{-1}$	41
2.23	The concept of work hardening during draw forming process	47
2.24	Mapping of plastic strain on bumper beam crash FE model (a) from the stamping FE model (b)	49
2.25	The effect of manufacturing process on crash results of (a) deformation mode without pre-simulation (left) and with pre-simulation (right), (b) contact force response, and (c) internal energy behaviour	50
2.26	Comparison between implicit and explicit time integration based on (a) the range of application and (b) cost versus complexity	52
3.1	Overall research methodology flowchart	56
3.2	True stress-strain curves of DP600 steel	61
3.3	Comparison of measured and predicted stress-strain curves by JC model of DP600 steel at different strain rates	64
3.4	Draw forming testing tools setup	66
3.5	Quasi-static crush test set up	67
3.6	Flowchart of FE model setup with overall methodology for draw forming simulation	69
3.7	The physical model of desired circular cup part	70
3.8	(a) The geometrical shape and (b) the cross-sectional front view with dimension of CAD model draw forming tools setup	71
3.9	Meshing of forming tools for open-die with double action draw mechanism	72
3.10	Comparison of blank meshing strategy from top view for the blank meshed using (a) automatic generated meshing and (b) bias meshing strategy	73

3.11	A close up view of free edges exist at the tip area where bending deformation occurred	74
3.12	(a) The formability region measured from final deformed shape, and (b) the top view of blank meshed using bias meshing strategy	75
3.13	Sectional view of boundary conditions applied on draw forming process	76
3.14	Mesh sensitivity analysis for selected region in the deformable blank	78
3.15	Comparison between experimental and FE simulation load displacement curve	80
3.16	Flowchart of FE crush simulation	82
3.17	Crush setup with cross sectional dimension	83
3.18	Meshed of the FE model	84
3.19	Sectional view of crash setup with boundary condition	85
3.20	Summary of mapping process	86
3.21	Comparison of impacted draw formed cup between (a) Experiment and (b) FE simulation	89
3.22	Comparison of crush load-displacement curve between experiment and FE simulation	89
4.1	Punch load-displacement curve throughout the drawing process at 8.333 mm/s	91
4.2	Load-displacement curve for draw formed circular cup at different punch speeds using JC	95
4.3	(a) The equivalent stress at fully loaded condition (b) residual stress, (c) residual strain of draw forming process at 0.833 mm/s	96
4.4	Punch speed effect on stress and strain level	97
4.5	Various locations selected for plastic strain rate measurement	98
4.6	The variation of thickness measured at different point for 9.5 mm depth draw formed circular cups at different punch speeds	99
4.7	Comparison of geometrical shape between ideal CAD and FE draw formed developed model	101
4.8	Percentage of thinning resulted from draw forming analysis of the final draw formed circular cup	101

4.9	Experimental load-displacement curve under quasi-static loading	103
4.10	Variation of thickness for cases studied as initial condition in crush analysis for (a) Case A and (b) Case B	105
4.11	Comparison of element at the sidewall area between both cases	106
4.12	Cross sectional view of the initial shape and final shape of the circular cup in crush analysis for (a) Case A and (b) Case B	107
4.13	Load-displacement curve comparison for case A and case B with experimental	108
4.14	The Von Mises stress contour plot of (a) case A and (b) case B after crush analysis without map at quasi-static loading	110
4.15	The plastic strain distribution with various locations for calculation of plastic strain rate for case A, (a) before and (b) after crush without mapping	111
4.16	The plastic strain distribution with various locations for calculation of plastic strain rate for case B, (a) before and (b) after crush without mapping	111
4.17	Calculated strain rates at various locations after crush analysis without mapping for both case A and case B	112
4.18	Comparison of thickness variation measured at different point for (a) Case A and (b) Case B	113
4.19	Energy absorption comparison between case A and case B	114
4.20	Mapping of preceding draw forming results on two types of geometrical cup shape model as initial condition for crush analysis	116
4.21	Cross-sectional view of the initial shape and final shape of the circular cup in crush analysis for (a) Case 1 and (b) Case 2	117
4.22	Load-displacement curve of FE quasi-static crush on ideal CAD (case 1) and draw formed (case 2) circular cup part with experiment	119
4.23	Load-displacement curve comparison of FE crush with and without mapping residual contour on ideal CAD and draw formed circular cup part with experiment	120
4.24	The Von Mises stress contour plot for (a) case 1 and (b) case 2 after crush analysis with map at quasi-static loading	121
4.25	The plastic strain distribution with various locations for calculation of plastic strain rate for case 1 (a) before and (b) after crush with map	122



4.26	The plastic strain distribution with various locations for calculation of plastic strain rate for case 2 (a) before and (b) after crush with map	123
4.27	Calculated strain rates at various locations after crush analysis with mapping for both case 1 and case 2	123
4.28	Comparison of thickness variation measured at different point for (a) Case 1 and (b) Case 2	124
4.29	Energy absorption of crush analysis performed with and without mapping	126
4.30	Load-displacement response under different loading conditions	127
4.31	Comparison of progressive deformation mode between quasi-static and dynamic crush loading	128
4.32	Von Mises stress contour plot of draw formed cup after crush analysis at (a) quasi-static loading and (b) dynamic loading	129
4.33	Plastic strain contour plot of draw formed cup after crush analysis at (a) quasi-static loading and (b) dynamic loading	130
4.34	Energy absorption at different crush loading with mapped residual contour	131

## LIST OF APPENDICES

APPENDIX	TITLE	PAGE
A	Load-displacement curve of draw forming process conducted at 0.0833, 0.833 and 8.333 mm/s	155
B	Mesh quality index for deformable blank	156
C	Comparison between FE stress strain behaviour and the global load-displacement response of the draw forming process	157
D	Strain rate curves at various locations for different punch speeds	158
E	Strain rate curves at various locations for crash analysis without mapping	160
F	Strain rate curves at various locations for crash analysis with mapping	161

## LIST OF ABBREVIATIONS

AHSS	-	Advanced High Strength Steel
ASTM	-	American Society for Testing and Materials
BHF	-	Blank Holder Force
BIW	-	Body in White
CAD	-	Computer-Aided Design
CEM	-	Crash Energy Management
CP	-	Complex phase
CPU	-	Central Processing Unit
CS	-	Cowper-Symond
DAD	-	Double Action Draw
DP	-	Dual Phase
FE	-	Finite Element
FEA	-	Finite Element Analysis
FEM	-	Finite Element Method
FLD	-	Forming Limit Diagram
HSLA	-	High Strength Low Alloy
HSS	-	High Strength Steel
IF	-	Interstitial-Free
IGES	-	Initial Graphics Exchange Specification
JC	-	Johnson-Cook
LCS	-	Low Carbon Steels
MS	-	Martensite steels
MIROS	-	Malaysia Institute of Road Safety Research
TRIP	-	Transformation induced plasticity
UTM	-	Universal Testing Machine
ZA	-	Zerilli-Armstrong

## LIST OF PUBLICATIONS

### JOURNAL:

1. Amman, R. M., Sivakumar, D., Abu-Shah, I. & Halim, M. F., 2018. Effects of Mapping on the Predicted Crash Response of Circular Cup-Shape Part. *Science & Technology Research Institute for Defence*, 11 (1), pp. 25-35.
2. Amman, R.M., Halim, M.F., Sivakumar, D., Abu-Shah, I., Sulaiman, S.N., Samekto, H. & Subramonian, S., 2018. Influences of Draw Forming Process on the Crash Analysis of a Circular Cup. *Journal of Advanced Manufacturing Technology*, 12, 1(2), pp. 547-560.
3. Amman, R. M., Halim, M. F., Sivakumar, D. & Abu-Shah, I., 2016. Influences Of Thickness And Geometrical Change From Draw Forming In Quasi-Static Axial Compression Simulation. *International Review on Modelling & Simulations*, 9 (6), pp. 442-449.

### PROCEEDING/CONFERENCE:

1. Amman, R. M., Halim, M. F., Sivakumar, D., Abu-Shah, I., Sulaiman, M.S. & Samekto, H., 2016. Study of thinning effect from deep drawing process on crash analysis. *Proceedings of Mechanical Engineering Research Day (MERD2016)*. Melaka, Malaysia, pp. 37-38, March 2016. UTeM.

# **CHAPTER 1**

## **INTRODUCTION**

### **1.1 Introduction**

This chapter presents the introduction and overview of the topic and contents covered in this thesis. This includes the background of the study, problem statement, research objectives, the scope of the study, significance of findings and thesis layout.

### **1.2 Background of Study**

In a study done by the Malaysia Institute of Road Safety Research (MIROS), it was found that the rate of road accidents in Malaysia is increasing annually with no sign of reduction (Abidin et al. 2012; Sarani et al. 2012). According to the United Nations World Health Organization's Global status report on road safety (Toroyan 2013; Toroyan 2015), Malaysia is the top among the Asian countries for having the highest road fatalities per 100,000 populations. For many years, road safety has become an international concern. Structures which operate under the risk of impact loadings, such as aircraft and vehicles, should consider the degree that able to protect the occupants from the effects of an accident which called crashworthiness. Crashworthiness is an ability of a structure to absorb the impact energy during collision or crash by controlled plastic deformations so that the energy transferred to the occupants will be minimized.

Nowadays, crash safety is an important issue in the automobile industry. It is very costly to study the crash event experimentally since it requires a lot of materials and many sensors to record huge data of impact loading. Therefore, since 1980's, crash studies by

using numerical simulation has been intensively applied with the aim of reducing both time and money (Schweizerhof et al. 1992). However, finite element (FE) simulation demands highly specialized analysts and super-computer processing power. Today, all advanced commercial FE software, such as Ls-Dyna, Abaqus, and HyperWorks, have the capabilities to simulate a transient dynamic condition in impact loading. Finite element method (FEM) has been extensively used to reduce the development time of a vehicle as well as to predict the crashworthiness or safety level of vehicles (Doğan 2009).

In current industrial practice of a crash simulation conducted in automotive industries, material is treated as the way it was delivered. This is because material does not undergo any mechanical or heat treatments. However, in reality, a deformed shape part has experienced significant changes of physical and mechanical properties which can influence the later crash response. The most obvious effects are thickness variation, residual stresses and strain effects which have an influence on the subsequent structural analysis such as crashworthiness assessment, fatigue life prediction, stiffness evaluation and structural strength evaluation (Wu-rong et al. 2009).

Figure 1.1 shows components that are used to build a car body structure made from different types of material. These automotive components are produced by different manufacturing process such as hydroforming and stamping which involve plastic deformation process. As can be seen, these structural components have undergone plastic deformation during metalworking affect the later crash response. It has been shown that incorporating these effects in the subsequent crash simulation of stamped components is important (Williams et al. 2010).




Figure 1.1: Components of AUDI A5 body structure (Kilic & Ozturk 2014)

As for lightweight vehicles, to ensure sufficient protection to the occupants during a collision, the car body structures are developed by using advanced materials to increase the strength-weight ratio. This leads to the development of advanced high strength steel (AHSS) which nowadays has been intensively applied in the auto bodies. Many materials have evolved in order to meet the lightweight and safety requirement such as magnesium, aluminium, low carbon steel and composite (Taub et al. 2007; Ghassemieh 2011). AHSS is no exception and has also shown its potential in order to maintain its low weight and cost characteristics, besides ensuring the safety of an occupant when a collision occurs. AHSS inherent high strength allows for thinner structural components making it lighter and contributing to a more fuel efficient vehicle (Kuziak et al. 2008). Among many types of AHSS material, the dual phase (DP) steel can attain very high strength while retaining moderate ductility compared to other materials. Ferrite-martensite DP steels 600 (DP600

steel) which has the ultimate tensile strength greater than 600 MPa, are one of the most popular AHSS used in the current vehicle production (Yu et al. 2009) to meet the enhanced government regulations and safety standards (Dong et al. 2014). The microstructure combination makes the DP steels to exhibit good formability with high strength based from the combination of soft ferritic matrix (provides good elongation) and islands of hard martensite (provides high strength). These characteristics make them ideal for energy absorption during an automotive crash.

The focus of this study is to investigate the crush response of a simple circular cup made of DP600 steel formed by using draw forming process. This study will cover numerical analysis using FEM and experimental studies to verify the simulation results.

### **1.3 Problem Statement**

In predicting the crashworthiness of a structural part, the current industrial finite element analysis (FEA) practice shows some disadvantages. Due to simplifications, the preceding deformation effects are often neglected in subsequent crush analysis and the advantage of mapping approach is still not fully appreciated among researchers. Dutton et al. (1999), Takashina et al. (2009) and Williams et al. (2010) investigated the forming effects on crash analysis without performing mapping process. The crush analysis commonly performed based on an assumption that the structural part has a uniform thickness, ideal geometrical shape and nominal mesh which are obtained directly from the computer-aided design (CAD) modelling process. Furthermore, the preceding residual stress and strain mapped contour of draw forming parts which make the change in work hardening are also not taken into consideration in the subsequent crush FEA. As a result, the actual crush testing which involve full vehicle structure does not get similar response when compared to FEA and thus lead to higher cost to repeat the crush test.